



BASECRETE™

Flexible Waterproof Bondcoat

Seam Strength, ASTM D751-06	COMPLIED		
	33.15 (lbs./2-inch width)		
Breaking Strength, ASTM D751-06	COMPLIED		
	Transverse	Longitudinal	
	181.8 psi	199.1 psi	
Dimensional Stability, ASTM D1204-2008	COMPLIED		
	+158 F	Transverse	-0.018
	(70C)	Longitudinal	-0.055
	-15F	Transverse	-0.16
	(-26C)	Longitudinal	-0.039
Waterproofness, ASTM D4068-1999	COMPLIED		
Shear Strength, ASTM C482-2022	COMPLIED		
	Ultimate Load (lbs)	2145.05	
	Shear Strength (psi)	143.0	
Fungus and Micro-Organism Resistance, ANSI A118.10-2014	COMPLIED		
Accelerated Aging, ASTM D 756-93			
Weatherometer, ASTM G155	PASS		
	No Cracking, cracking, spalling, or other surface deteriorations		
Freeze-Thaw, ASTM C 67	PASS		



BASECRETE™

Flexible Waterproof Bondcoat

Bond-strength, ASTM C 297	PASS
Control	116 (psi)
After Accelerated Aging	370 (psi)
After Freeze-Thaw	423 (psi)
Abrasion, ASTM C501 / C957	PASS
Percolation, AC39 / ASTM E96	PASS
	0.1
Water-absorption, ASTM D 570	PASS
	10.1 (% wt.)
Chemical-resistance, ASTM d 2299	PASS
Concentrated Load, AC39 4.12	PASS
	No tearing or cracking
Foot Traffic Resistance, FM 4470	PASS
	No tearing or cracking
NSF/ANSI/CAN 61	PASS
ASTM E-84	PASS
	CLASS A
Flame Spread Index	(FSI) 0
Smoke Developed Index	(SDI) 10

Basecrete Technologies
8255 Consumer Ct, Lot 25
Sarastoa, FL 34240

(941)312-5142
info@basecreteusa.com